

# **DURO-LAST<sup>®</sup> VB PRIMER**

## **DESCRIPTION:**

Duro-Last<sup>®</sup> VB Primer is a solvent-based primer composed of a blend of natural resins and synthetic rubber. Duro-Last VB Primer is designed to enhance the adhesion of Duro-Last Vapor Barrier to a variety of surfaces such as structural concrete, gypsum, lightweight concrete, wood, and masonry.

## **ORDERING:**

Duro-Last VB Primer is ordered in individual 5-gallon pails.

• 33-lb. pail (Item #1345)

## STORAGE AND HANDLING

Product can be stored for up to 36 months in original sealed containers. Store in a cool, well-ventilated area between 14 and 75° F. Keep away from any source of heat, dampness, humidity, oxidizing agents or direct sunlight.

Product is flammable prior to curing. Keep away from open flames and any other source of ignition.

#### **PRECAUTIONS:**

- 1. Read Safety Data Sheets (SDS) prior to using.
- 2. Wear proper personal protective equipment, such as gloves and eye protection, per the SDS.
- 3. This product is not intended for use with any Duro-Last membrane.

#### INSTALLATION:

- 1. Limitations
  - a. The minimum ambient and surface temperature before application should be 14° F and rising.
  - b. Apply to a clean and structurally sound substrate.
- 2. Shake product thoroughly prior to application.
- 3. Apply to deck at a rate of 75 125 sq. ft. per gallon using either a brush or roller.
- 4. Do not install Duro-Last Vapor Barrier until Duro-Last VB Primer has completely dried. **Do not accelerate drying by use of heat.**



	Standards	Results
Specific gravity at 68° F	-	6.59 lbs./gal <sup>1</sup>
Color	-	Red
Solids by weight	-	24% <sup>1</sup>
Viscosity, Brookfield at 77° F	-	200 cP <sup>1</sup>
Set time	-	Between 15 and 60 minutes, depending on temperature and quantity applied.
Application temperature	-	14° F and rising
	-	75 – 125 sq. ft. per gallon

Nominal.

## CLEANING:

Tools can be cleaned with petroleum solvents such as mineral spirits, Varsol<sup>™</sup>, xylene, etc. **Do not allow cleaning solvents to come in contact with any Duro-Last membrane.**